



Plastique CAREFOAM

FICHE TECHNIQUE

Polypropylène copolymère

Densité 910 kg/m³

LE PPC CARFOAM[®] est Polyéthylène haute densité spécialement développé pour l'orthopédie.
Il est caractérisé par un retrait Isotrope et faible

Key benefits

Polypropylene homopolymer (PPH)
Excellent thermoforming
Chemical and corrosion resistant

General application

Orthopaedics

	Test method	Unit	Value
General properties			
Density	DIN 53479	g/cm ³	0,91
Filler content		%	
Mechanical Properties			
Tensile modulus	ISO 527	MPa	1600
Tensile strength	ISO 527	MPa	36
Elongation at break	ISO 527	%	>50
Flexural modulus	ISO 178	MPa	
Charpy notched impact strength at 23°C	ISO 179	kJ/m ²	7
Charpy unnotched impact strength at 23°C	ISO 179	kJ/m ²	
Hardness	ISO 868	Shore D	75
Thermal properties			
Melting temperature	ISO 3146	°C	165
Vicat softening temperature - A50	ISO 306/A50	°C	
Vicat softening temperature - B50	ISO 306/B50	°C	95
Heat deflection temperature B (0.45 MPa)	ISO 75B	°C	109
Heat deflection temperature A (1.80 MPa)	ISO 75A	°C	
Service temperature (intermittent)		°C	135
Service temperature (long term)		°C	0 ... 100
Other properties			
Surface resistivity	LabeOHM	Ω	>10 ¹⁴
Water absorption	24h/RT	%	<0,01
Flammability (thickness 3 mm)	UL94		HB
Mould shrinkage	Compared to a reference form	%	Longitudinal: / Transverse: /

InnOfOam

Contact :
Jean POUBLAN
Tutuania
Quartier PENA
64240 HASPARREN
Tel 00 33 (0)9 52 20 37 14
Mobile 00 33 (0)6 71 37 37 35
Fax 00 33 (0)9 57 20 37 14
jean.pouban@innofoam64.com
www.carefoam.fr

Siège social :
Domaine Coulom - AUBOUS
64330 GARLIN
RCS : PAU 451 700 306 (2004 B 43)
SIRET : 451 700 306 00017
N° TVA INTRA : FR66451700306